

WOVEN FABRICS: PARA ARAMID PRODUCT RANGE

STYLE	WEIGHT (g/m ²)	WEIGHT (oz/yd ²)	YARN COUNT (TEX)		THREADS PER CM		STRUCTURE	WEAVE	THICKNESS (mm)	WIDTH (mm)
			WARP	WEFT	WARP	WEFT				
AK220	75	2.21	40.5	40.5	8.7	8.7	Wa 50%, We 50%. High Modulus	Plain	0.10	1000
AK340	115	3.39	40.5	40.5	13	13	Wa 50%, We 50%. High Modulus	5 end Satin	0.25	1000
AK340	115	3.39	40.5	40.5	13	13	Wa 50%, We 50%. High Modulus	5 end Satin	0.25	1200
AK342	115	3.39	40.5	40.5	13.2	13.2	Wa 50%, We 50%. High Modulus	Plain	0.25	1200
AK500	168	4.95	161	161	5.1	5.1	Wa 50%, We 50%. High Modulus	Plain	0.25	1000
AK500	168	4.95	161	161	5.1	5.1	Wa 50%, We 50%. High Modulus	Plain	0.25	1270
AK500	168	4.95	161	161	5.1	5.1	Wa 50%, We 50%. High Modulus	Plain	0.25	1350
AK281	173	5.10	121	121	6.7	6.7	Wa 50%, We 50%. High Modulus	Plain	0.25	1000
AK502	175	5.16	168	168	5.1	5.1	Wa 50%, We 50%. Std Modulus	2X2 Twill	0.30	1000
AK328SM	220	6.49	168	168	6.5	6.5	Wa 50%, We 50%. Std Modulus	Plain	0.37	1000
AK901	310	9.14	336	336	4.49	4.33	Wa 51%, We 49%. Std Modulus	5HSatin	0.40	1270
AK900	320	9.44	252	252	6.3	6.3	Wa 50%, We 50%. High Modulus	5HSatin	0.53	1270
AK1350	458	13.51	242	242	10.25	8.7	Wa 54%, We 46%. High Modulus	4X4 Basket	0.62	1270

NOTE: PRODUCTS CAN BE MANUFACTURED AT ALTERNATE WIDTHS UPON REQUEST