

WOVEN FABRICS: CARBON FIBRE PRODUCT RANGE

STYLE	WEIGHT (g/m ²)	WEIGHT (oz/yd ²)	YARN COUNT (TEX)		THREADS PER CM		STRUCTURE	WEAVE	THICKNESS (mm)	WIDTH (mm)
			WARP	WEFT	WARP	WEFT				
AC227	92	2.71	68(1K)	68(1K)	6.90	6.90	Warp 50%, Weft 50%.	Plain	0.11	1000
AC209	94	2.77	68(1K)	68(1K)	7.00	7.00	Warp 50%, Weft 50%.	Plain	0.11	1000
AC226	160	4.72	200(3K)	200(3K)	4.00	4.00	Warp 50%, Weft 50%.	Plain	0.25	1000
AC220	198	5.84	200(3K)	200(3K)	5.00	5.00	Warp 50%, Weft 50%.	Plain	0.25	1000
AC221	198	5.84	200(3K)	200(3K)	5.00	5.00	Warp 50%, Weft 50%.	2/2 Twill	0.25	1000
AC238	200	5.90	800(12K)	10 (Polyester)	2.46	2.00	Warp 99%, Weft 1%. Unidirectional	Plain	0.3	500
AC228U	227	6.69	800 (12K)	10 (Polyester)	2.55	2.00	Warp 99%, Weft 1%. Unidirectional	Plain	0.26	610
AC224	303	8.94	800 (12K)	10 (Polyester)	3.70	2.00	Warp 99%, Weft 1%. Unidirectional	Plain	0.4	500
AC229	416	12.27	1600(24K)	10 (Polyester)	2.56	3.15	Warp 99%, Weft 1%. Unidirectional	Plain	0.6	500
CAH300	190	5.60	200(3K), 161	200(3K), 161	2.6, 2.6	2.6, 2.6	Wa 50%, We 50%. Carbon Aramid	2x2 Twill	0.30	100

NOTE: PRODUCTS CAN BE MANUFACTURED AT ALTERNATE WIDTHS UPON REQUEST