

WOVEN TAPES: JOINING & SCRIM PRODUCT RANGE

STYLE	WEIGHT (g/m ²)	WEIGHT (oz/yd ²)	YARN COUNT (TEX)		THREADS PER CM		STRUCTURE	WEAVE	THICKNESS (mm)	WIDTH (mm)
			WARP	WEFT	WARP	WEFT				
AP520	105	3.10	29.5x2	29.5x2	8.7	8.3	Warp 51%, Weft 49%. Heatset Polyester	Plain	0.45	100
AT311	150	4.42	68x1	68x1	7.1	6.7x2	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	25
AT3115	150	4.42	68x1	68x1	7.1	6.7x2	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	38
AT312	150	4.42	68x1	68x1	7.1	6.7x2	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	50
AT313	150	4.42	68x1	68x1	7.1	6.7x2	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	75
AT314	150	4.42	68x1	68x1	7.1	6.7x2	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	100
AT316	155	4.57	68x1	(68x1)x2	7.5	6.8	Warp 35%, Weft 65%. Woven Selvedge	Plain	0.17	150
AT308	178	5.25	136x1	136x1	6.7	6.7	Warp 50%, Weft 50%. Feathered Selvedge	Plain	0.20	200
AT749	220	6.49	68x1	34x1	20.5	10.6x2	Warp 65%, Weft 35%. Woven Selvedge	Plain	0.18	50
AT749	220	6.49	68x1	34x1	20.5	10.6x2	Warp 65%, Weft 35%. Woven Selvedge	Plain	0.18	75
AT352	300	8.85	136x1	(136x1)x2	7.1	6.8x2	Warp 34%, Weft 66%. Woven Selvedge	Plain	0.27	50

NOTE: PRODUCTS CAN BE MANUFACTURED AT ALTERNATE WIDTHS UPON REQUEST