

WOVEN ROVINGS: BI DIRECTIONAL PRODUCT RANGE

STYLE	WEIGHT (g/m2)	WEIGHT (oz/yd2)	YARN COUNT (TEX)		THREADS PER CM		STRUCTURE	WEAVE	THICKNESS (mm)	WIDTH (mm)
			WARP	WEFT	WARP	WEFT				
AR104	250	7.37	300	300	4.33	3.93	Warp 52 %, Weft 48 %	Plain	0.23	1000
AR141	290	8.55	300	300	5.60	4.00	Warp 58 %, Weft 42 %	Plain	0.30	1000
AR146	290	8.55	600	300	3.15	3.15	Warp 67 %, Weft 33 %	Plain	0.30	1000
AR103	320	9.44	600	600	2.46	2.56	Warp 49 %, Weft 51 %	Plain	0.30	1230
AR145	398	11.74	600	1150	3.15	1.77	Warp 48 %, Weft 52 %	Plain	0.50	1000
AR115	400	11.80	1150	1800	1.50	1.20	Warp 44%, Weft 56 %	Plain	0.60	1000
AR117	450	13.27	1200	600	2.46	2.36	Warp 68 %, Weft 32 %	Plain	0.50	1000
AR119	450	13.27	1200	600	2.50	2.50	Warp 67 %, Weft 33 %	Plain	0.50	1550
AR128	500	14.74	900	1800	2.48	1.58	Warp 44%, Weft 56 %	Plain	0.50	1250
AR108	550	16.22	1200	1200	2.95	1.57	Warp 65 %, Weft 35 %	Plain	0.60	1200
AR111	588	17.34	1150	1150	2.46	2.46	Warp 50 %, Weft 50 %	Plain	0.60	1000
AR110	620	18.28	1150	1150	2.46	2.75	Warp 47 %, Weft 53 %	Plain	0.50	1000
AR106*	630	18.58	1200	1800	2.95	1.58	Warp 55 %, Weft 45 %.	Plain	0.60	1000
AR105*	830	24.48	2400	2400	1.97	1.58	Warp 55 %, Weft 45 %.	Plain	0.85	1000
AR125	1140	33.62	1200	4800	3.00	1.60	Warp 32 %, Weft 68 %	Plain	1.20	1000
AR150	1160	34.21	2400	2400	2.46	2.36	Warp 51 %, Weft 49 %	Plain	1.00	1000

NOTE: PRODUCTS CAN BE MANUFACTURED AT ALTERNATE WIDTHS UPON REQUEST

NOTE: PRODUCTS MARKED WITH * HAVE LLOYDS APPROVAL