

WOVEN TAPES: PIPE INDUSTRY SPECIFIC PRODUCT RANGE

STYLE	WEIGHT (g/m ²)	WEIGHT (oz/yd ²)	YARN COUNT (TEX)		THREADS PER CM		STRUCTURE	WEAVE	THICKNESS (mm)	WIDTH (mm)
			WARP	WEFT	WARP	WEFT				
AT270	270	7.96	300	136x1	3.9	4.3x2	Warp 50%, Weft 50%	Plain	0.2	25
AT270	270	7.96	300	136x1	3.9	4.3x2	Warp 50%, Weft 50%	Plain	0.2	50
AT270	270	7.96	300	136x1	3.9	4.3x2	Warp 50%, Weft 50%	Plain	0.2	100
AT290	290	8.55	300	300	4.3	2.6x2	Warp 45%, Weft 55%	Plain	0.25	25
AT290	290	8.55	300	300	4.3	2.6x2	Warp 45%, Weft 55%	Plain	0.25	50
AT290	290	8.55	300	300	4.3	2.6x2	Warp 45%, Weft 55%	Plain	0.25	100
AT360	360	10.62	600	900	3.2	1.80	Warp 54%, Weft 46%	Plain	0.35	100
AT360	360	10.62	600	900	3.2	1.80	Warp 54%, Weft 46%	Plain	0.35	160
AT365	380	11.21	600	1150	2.95	1.69	Warp 48%, Weft 52%	Plain	0.35	100
AT365	380	11.21	600	1150	2.95	1.69	Warp 48%, Weft 52%	Plain	0.35	160
AT145	398	11.74	600	1150	3.15	1.77	Warp 48%, Weft 52%	Plain	0.5	150
AT142	410	12.09	600	1200	2.48	1.97	Warp 39%, Weft 61%	Plain	0.5	200
AT420	420	12.39	300	300	7	3.54x2	Warp 50%, Weft 50%	2x2 Broken Twill	0.57	100
AT147	475	14.01	600	1800	3.15	1.60	Warp 40%, Weft 60%	Plain	0.5	200
AT143	493	14.54	600	1150	2.46	2.76	Warp 46%, Weft 54%	Plain	0.5	100
AT580	580	17.10	1200	1200	2.6	2.20	Warp 54%, Weft 46%	Plain	0.5	160

NOTE: PRODUCTS CAN BE MANUFACTURED AT ALTERNATE WIDTHS UPON REQUEST